



MEDOP-**Tex Classic**



Body protection: single use suits

Description and composition:

Single use suit made of 55 g SMS.


Has a **three-piece hood** and elastic adjustment to ankles, wrists and back. **One-direction zipper** with single flap and adhesive protective tape.

V-shaped reinforced stitching in crotch. Stitched seams

Colour: WHITE.

Sizes: S, M, L, XL, XXL and XXXL.

CE marking: TYPE 6 AND 5.



Stitched seams




Zipper with protective adhesive strip















Elastically adjusts to ankle, wrists and back

Ref:	Size	Height	Chest	Weight
912.129	S	164 to 170 cm	84 to 92 cm	187 g
912.130	M	170 to 176 cm	92 to 100 cm	187 g
912.131	L	176 to 182 cm	100 to 108 cm	187 g
912.132	XL	182 to 188 cm	108 to 116 cm	187 g
912.133	XXL	188 to 194 cm	116 to 124 cm	187 g
912.134	XXXL	194 to 200 cm	124 to 132 cm	187 g



Body protection: single use suits

Standard and certification	<div style="display: flex; justify-content: space-around; align-items: center;"> <div style="text-align: center;">  <p>Chemical risk</p> </div> <div style="text-align: center;">  <p>Particle-tight</p> </div> <div style="text-align: center;">  <p>Chemical splash-proof</p> </div> <div style="text-align: center;">  <p>Electrostatic properties</p> </div> <div style="text-align: center;">  <p>Radioactive Particle-tight</p> </div> </div> <p style="text-align: center;">Protective clothing General requirements EN ISO 13688-2013</p> <div style="display: flex; justify-content: space-around; align-items: center;"> <div style="text-align: center;">  <p>EN ISO 13982-1/04 + A1/10 EN 13034/05 + A1/09 Type 5</p> </div> <div style="text-align: center;">  <p>Type 6 EN 1149-5/08</p> </div> <div style="text-align: center;">  <p>EN 1073-2/02 Class 1</p> </div> </div>																						
Applications	Food and beverage industry Petrol and gas activities Painting Asbestos handling Electronics	Automotive industry Spray application of paint Surface treatments																					
Conservation Storage - Expiry	The article must be kept in a cool, dry, dark place. This product should be used within five years of the manufacture date shown on the label.																						
Directions Use Maintenance and cleaning	Ensure size is adequate for user. Do not modify the product in any way. <div style="display: flex; justify-content: space-around; align-items: center; margin-top: 10px;"> <div style="text-align: center;">  <p>Do not wash</p> </div> <div style="text-align: center;">  <p>Do not iron</p> </div> <div style="text-align: center;">  <p>Do not tumble-dry</p> </div> <div style="text-align: center;">  <p>Do not dry-clean</p> </div> </div>																						
Presentation	Individually packed: 1 unit 50 unit carton. (52 x 32 x 58)																						
Bar code	<table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th></th> <th>BAR CODE</th> <th>CARTON BAR CODE</th> </tr> </thead> <tbody> <tr><td>912.129</td><td>8423173880248</td><td>18423173880245</td></tr> <tr><td>912.130</td><td>8423173880255</td><td>18423173880252</td></tr> <tr><td>912.131</td><td>8423173880262</td><td>18423173880269</td></tr> <tr><td>912.132</td><td>8423173880279</td><td>18423173880276</td></tr> <tr><td>912.133</td><td>8423173880286</td><td>18423173880283</td></tr> <tr><td>912.134</td><td>8423173880293</td><td>18423173880290</td></tr> </tbody> </table>			BAR CODE	CARTON BAR CODE	912.129	8423173880248	18423173880245	912.130	8423173880255	18423173880252	912.131	8423173880262	18423173880269	912.132	8423173880279	18423173880276	912.133	8423173880286	18423173880283	912.134	8423173880293	18423173880290
	BAR CODE	CARTON BAR CODE																					
912.129	8423173880248	18423173880245																					
912.130	8423173880255	18423173880252																					
912.131	8423173880262	18423173880269																					
912.132	8423173880279	18423173880276																					
912.133	8423173880286	18423173880283																					
912.134	8423173880293	18423173880290																					

Behaviour - Levels and classes		
EN 1149-5		
TEST	RESULT	CLASS
Surface resistivity (EN 1149-1)	7,3 x 10 (7)	pass
EN 13034 + EN 13982-1 + EN 1073-2		
TEST	RESULT	CLASS
Resistance to penetration (EN 6530)		
H2SO4 30%	0,00%	3
NaOH 10%	0,00%	3
O-xylene	21,50%	NC
Butan 1 ol	17,10%	NC
Repellency to Liquid (EN 6530)		
H2SO4 30%	92,00%	2
NaOH 10%	96,70%	3
O-xylene	3,40%	NC
Butan 1 ol	18,60%	NC
Abrasion Resistance (EN 530 method 2)		
	350 cycles	2
Trapezoidal tear resistance (EN ISO 9073-4)		
	68 N wrap 33,8 N weft	2
Tensile strenght (EN ISO 13934-1)		
	120 N warp 54 N weft	1
Puncture resistance (EN 863)		
	6,1 N	1
Flex cracking resistance (EN ISO 7854 method B)		
	No damage after 1500 cycles	4
Light spray test (EN 13034 - EN 468)		
	No stain on the witness coveralls	pass
Inward leakage test (EN 13982-2)		
	Ljmn 82/90 <30% Ls 8/10 < 15%	pass-CLASS 1
Seam strenght <8EN ISO 13935-2) Serged seam		
	78 N	3
Aromatic amines derived from azo dyes		
	Not detectable	pass