



MEDOP-**Tex Plus**



Body protection: single use suits

Description and composition:

Single use suit made of 65 g microporous film.

Has a **three-piece hood** and elastic adjustment to ankles, wrists and back. **Two-direction zipper with double flap** and adhesive protective tape.

V-shaped reinforced stitching in crotch. Stitched seams

Colour: WHITE.

Sizes: S, M, L, XL, XXL and XXXL.

CE marking: TYPE 6-B AND 5-B.



Stitched seams




Two-direction zipper
+ adhesive protective tape













Elastically adjusts to ankle,
wrists and back

Ref:	Size	Height	Chest	Weight
912.111	S	164 to 170 cm	84 to 92 cm	221 g
912.112	M	170 to 176 cm	92 to 100 cm	221 g
912.113	L	176 to 182 cm	100 to 108 cm	221 g
912.114	XL	182 to 188 cm	108 to 116 cm	221 g
912.115	XXL	188 to 194 cm	116 to 124 cm	221 g
912.116	XXXL	194 to 200 cm	124 to 132 cm	221 g



Body protection: single use suits

Standard and certification	<div style="display: flex; justify-content: space-around; align-items: center;"> <div style="text-align: center;">  <p>Chemical risk EN ISO 13982-1/04 +A1/10 EN 13034/05 + A1/09</p> </div> <div style="text-align: center;">  <p>Particle-tight Type 5B</p> </div> <div style="text-align: center;">  <p>Chemical splash-proof Type 6B</p> </div> <div style="text-align: center;">  <p>infective agents EN 14126/03</p> </div> <div style="text-align: center;">  <p>Electrostatic properties EN 1149-5/08</p> </div> <div style="text-align: center;">  <p>Radioactive Particle-tight EN 1073-2/02 Class 1</p> </div> </div> <p>Protective clothing General requirements EN ISO 13688-2013</p>																						
Applications	Food and beverage industry Petrol and gas activities Asbestos handling Electronics	Automotive industry Spray application of paint Surface treatments																					
Conservation Storage - Expiry	The article must be kept in a cool, dry, dark place. This product should be used within five years of the manufacture date shown on the label.																						
Directions Use Maintenance and cleaning	Ensure size is adequate for user. Do not modify the product in any way. <div style="display: flex; justify-content: space-around; margin-top: 10px;"> <div style="text-align: center;">  <p>Do not wash</p> </div> <div style="text-align: center;">  <p>Do not iron</p> </div> <div style="text-align: center;">  <p>Do not tumble-dry</p> </div> <div style="text-align: center;">  <p>Do not dry-clean</p> </div> </div>																						
Presentation	Individually packed: 1 unit Carton of 50 units. (52 x 32 x 48)																						
Bar code	<table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th style="width: 10%;"></th> <th style="width: 45%;">BAR CODE</th> <th style="width: 45%;">CARTON BAR CODE</th> </tr> </thead> <tbody> <tr><td>912.111</td><td>8423173880064</td><td>18423173880061</td></tr> <tr><td>912.112</td><td>8423173880019</td><td>18423173880016</td></tr> <tr><td>912.113</td><td>8423173880071</td><td>18423173880078</td></tr> <tr><td>912.114</td><td>8423173880040</td><td>18423173880047</td></tr> <tr><td>912.115</td><td>8423173880101</td><td>18423173880108</td></tr> <tr><td>912.116</td><td>8423173880118</td><td>18423173880115</td></tr> </tbody> </table>			BAR CODE	CARTON BAR CODE	912.111	8423173880064	18423173880061	912.112	8423173880019	18423173880016	912.113	8423173880071	18423173880078	912.114	8423173880040	18423173880047	912.115	8423173880101	18423173880108	912.116	8423173880118	18423173880115
	BAR CODE	CARTON BAR CODE																					
912.111	8423173880064	18423173880061																					
912.112	8423173880019	18423173880016																					
912.113	8423173880071	18423173880078																					
912.114	8423173880040	18423173880047																					
912.115	8423173880101	18423173880108																					
912.116	8423173880118	18423173880115																					

Behaviour - Levels and classes		
TEST	RESULT	CLASS
EN 1149-5		
Surface resistivity (EN 1149-1)	2,49 x 10(9)	pass
EN 13034 + EN 13982-1 + EN 1073-2		
Resistance to penetration (EN 6530)		
H2SO4 30%	0,00%	3
NaOH 10%	0,00%	3
O-xylene	21,50%	3
Butan 1 ol	17,10%	3
Repellency to Liquid (EN 6530)		
H2SO4 30%	95,00%	3
NaOH 10%	95,10%	3
O-xylene	91,90%	2
Butan 1 ol	94,20%	2
Abrasion Resistance (EN 530 method 2)	300 cycles	2
Trapezoidal tear resistance (EN ISO 9073-4) 26,5 N wrap 45,3 N weft		2
Tensile strenght (EN ISO 13934-1) 55 N warp 100 N weft		1
Puncture resistance (EN 863)	14,4 N	2
Flex cracking resistance (EN ISO 7854 method B)	No damage after 10000 cycles	6
Light spray test (EN 13034 - EN 468)	No stain on the witness coveralls	pass
Inward leakage test (EN 13982-2)	Ljmn 82/90 <30% Ls 8/10 < 15%	pass- CLASS 1
Thermal resistance (EN31092-1994): M2 k/W	Rct: 0,013	
Water vapour resistance (EN31092:1994): M2 Pa/WRect: 10.96		